

TECHNICAL DATA SHEET

0893550

PTFE lubricant spray

Transparent, dirt-resistant dry lubricant for light to medium loads

Fields for application:

Suitable for dry lubrication of friction points

Properties:

- Remedies squeaking, creaking and stiff movement
- Dry lubrication
- Film thickness of 10 µm allows use for even the smallest tolerances (precision engineering)
- Very high resistance
- Silicone-free
- Mineral-oil-free

Application:

- Shake briefly before use. Spray a thin layer onto friction points or joints and allow to dry
- Drying time for a thin application: approx. 1 - 2 mins.
- Drying time for a thicker application approx. 5 mins.

Technical data:

Temperature resistance	365°C
Boiling point/boiling range	-44°C (initial boiling point of the propellant gas)
Density	0.6 g/cm ³ at 20°C (density of the aerosol)
PTFE content (dry film)	Approx. 52%
Water solubility	Cannot be mixed after all volatile matter has evaporated

TECHNICAL DATA SHEET

Notes:

Smokers must wash their hands after use. Smoking contaminated tobacco products may cause health-related issues.

This advice is based on our own research and experience. It is presented in good faith and may be considered reliable. However, due to the diverse processing, application and handling possibilities the information provided may not be considered legally binding. The same applies to the information provided by our technical and commercial customer service.

We recommend the users of our products to perform their own tests in order to determine whether our products are appropriate for the respective use and environment. We guarantee the consistent quality of our products. We reserve the right to implement technical changes and improvements.