


Application Specific Probes The key to successful coating measurement

Probes are the most important component of systems used to measure coating thickness with either magnetic, magnetic induction and eddy current methods. This is the reason significant efforts and resources are expended by FISCHER for the development and quality control of probes.

- FISCHER probes are adapted and optimized for the application!
 This guarantees accurate and reliable measurement results.
- FISCHER probes are dependable and durable!
 The probes are long lasting and durable, even when measurements are to be per-

formed which test their "wear resistance".


FISCHER probes are reliable!
 This is due to their advanced design, their careful assembly and use of high quality components.



Measuring Methods and Processing Measuring Signals


This technical information material introduces standard magnetic probes, magnetic induction probes and eddy current

probes to measure coating thickness. The fundamental, physical principles are explained below.




Magnetic Method

A permanent magnet produces a continuous magnetic field (DIN EN ISO 2178) the strength of which depends upon the thickness of the coating to be measured (Ni/Fe), or the distance between probe and substrate (NF/Fe). The strength of the magnetic field is measured with an appropriate sensor and the coating thickness is calculated from this information.



Magnetic Induction Method

The energizing alternating current produces a low frequency magnetic field (DIN EN ISO 2178) the strength of which depends upon the distance between the probe and the substrate. The magnetic flux density is measured by means of a pickup coil. The induced measurement signal obtained is converted into the coating thickness value through translation using the characteristic probe output function.




Eddy Current Method

The energizing current produces a high frequency magnetic field (DIN EN ISO 2360) which induces eddy currents in the substrate material (or in the coating material to be measured with the modified test method). The magnitude of the induced eddy currents depends upon the distance (coating thickness) between probe and substrate. The measurement signal is then evaluated as a function of the eddy currents produced.

Signal Processing

The electrical signal transmitted from the probe is processed by the measuring instrument and digitized. The processed signal is normalized to standardize the possible measuring range and to minimize any disturbing effects. With type E series smart probes this signal is then converted

through a characteristic probe output function which is stored in the memory chip of the probe connector, into a measurement value indicative of the measured coating thickness. With other (older) probes this characteristic function is stored in the measuring system.



Normalization of the probe signal is performed as follows:

$$X_n = \frac{X - X_0}{X_S - X_0}$$

The variables are:


X₀: probe signal from the uncoated sub-

X_s: probe signal from infinitely thick coating (saturation thickness)

X : probe signal from the measured coating thickness d.

The normalized signal X_n therefore is only able to assume values between 0 and 1.

 ${\rm X}_{\rm n}$ is then converted over the characteristic probe output function into the measured coating thickness value d.



The characteristic probe output function is stored in the memory chip of the probe connector and thus the probe contains all information required for the measurement. The operator simply recalls the measurement application; the system is ready to measure immediately. Measurements performed at intermittent time intervals therefore always start with the same reference value.

Technical Data and Selection of Probes



Tables for the selection of probes

The solution for many different coating thickness measurements with the magnetic, magnetic induction or eddy current method depends upon the selection of the "correct" probe. Often the measurement accuracy and measurement precision can be optimized by using a more suitable probe.

The following tables provide an overview of all standard probes. The technical data and values shown should facilitate selection of the probe best suited for your specific application. Explanations are listed below.

Explanation to the Technical Data

Measurement Range

The measurement range of the probe specifies the limits of the coating thickness that can be measured.

Measurement Accuracy

(DIN 55350 section 13, paragraph 2.1.1) The measurement accuracy has been determined with plastic foils of specific thickness. The specified value $u_{\rm S}$ corresponds to the measured systematic deviation (bias) between the measured thickness value and true thickness value of the calibration foil.

This parameter is a quality indicator showing how good the measurement signal from the probe has been converted over the characteristic probe output function stored in the memory of the probe into a corresponding coating thickness value.

Measurement Precision

(DIN 55350 section 13, paragraph 2.1.2.2) The value shown represents the measured standard deviation, which can be obtained by replicate measurements on an appropriate plastic foil.

The measurement uncertainly of a group mean measurement is then calculated according to DIN 1319 section 3 as follows:

$$u_z = \frac{t}{\sqrt{n}} \cdot s$$

For group size n=10 a student's t value of 2.5 applies.

Comments

The most important quality attributes of a measurement method are mainly measurement accuracy, measurement precision and measurement uncertainty.

The measurement uncertainty u (DIN 55350 section 13, par 4.1) is calculated from $\rm u_Z$ and $\rm u_S$ according to:


$$u = \sqrt{u_z^2 + u_s^2}$$

The measurement methods utilized here yield different values of u_Z and u_S over the complete measurement range of a probe. Within the so called linear range of the probe (see graph to the right), their values are almost constant. If the same value applies for the hyperbolic as well as logarithmic range, the hyperbolic measure-

ment uncertainty is not stated.

The values of u_s and u_z are listed in the following tables as either absolute values (for example: 1 μ m) or as relative values referring to the measurement value (for example: 0.5 %).

The values listed represent the optimum values which have been determined with FISCHER standards. In many cases marginal values may be obtained due to less than ideal surface conditions. FISCHER cannot be held accountable for marginal values obtained from rough surfaces.



Test Specimen Geometry

For the above mentioned measurement methods the geometry of the measurement area influences the measurement value. The following tables list two values for each geometry dependent factor (except for substrate thickness).

The upper value indicates the smallest diameter of the object that can be measured, for which the curvature dependent measurement bias will not exceed 10% of the true value. Calibration was performed on a flat surface of "infinite" area using the same substrate material.

The lower value indicates the limiting diameter at which if exceeded a measurement is no longer possible due to the geometry of the probe (for example: the probe tip no longer contacts the surface), or at which the measurement signal is too small due to insufficient material volume.

Measurement point



convex curvature diameter



concave curvature diameter



diameter of the test area



substrate thickness D

The limit value D indicates the substrate thickness below which the measurement value deviates more than 10% from an "infinitely" thick base metal.

The limiting values have been determined with a foil thickness, which produces a reading which is approximately in the center of the probe measuring range.

With increasing measured thickness the 10% bias error is obtained with smaller curvature diameters, and respectively smaller substrate thicknesses.

Note regarding probe designations:			Magauroment point	
L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m.	Description Order Number	Measurement accuracy*	Measurement point Ø for 10% error min. Ø	
F: Measuring element protected against moist, aggressive media.		u _s	— ø → min. Ø	
T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible.	Measurement	Measurement precision*	Ø for 10% error	
* Note: Probe capability (accuracy and precision) tested under controlled conditions.	range	s	min. Ø	
	EGA1.3 602-118	0-50 μm : 0.25 μm 50-1000 μm : 0.5 % 1000-1500 μm : < 2.5 %	ø : 14 mm (550 mils) min. ø : 2 mm (80 mils)	
	0-1500 μm 0-60 mils	0-50 μm : 0.1 μm 50-1500 μm : 0.2 %	ø : 36 mm (1.4") min. ø : 10 mm (400 mils)	
	EGAW1.3 602-119	0-50 μm : 0.25 μm 50-1000 μm : 0.5 % 1000-1500 μm : < 2.5 %	ø : 14 mm (550 mils) min. ø : 1 mm (40 mils)	
	0-1500 μm 0-60 mils	0-50 μm : 0.1 μm 50-1500 μm : 0.2 %	ø : 36 mm (1.4") min. ø : 18 mm (700 mils)	
	EGAB1.3 601-793 EGAB1.3.L 602-794 EGAB1.3.T 602-359	0-100 μm : 0.5 μm 100-1000 μm : 0.5 % 1000-2000 μm : < 3 %	ø : 18 mm (700 mils) min. ø : 2 mm (80 mils)	
	0-2000 μm 0-80 mils	0-50 μm : 0.1 μm 50-2000 μm : 0.2 %	ø : 35 mm (1.4") min. ø : 10 mm (400 mils)	
	EGABW1.3 601-964 EGABW1.3.L 602-925	0-100 μm : 0.5 μm 100-1000 μm : 0.5 % 1000-2000 μm : < 3 %	ø : 16 mm (640 mils) min. ø : 1 mm (40 mils)	
	0-2000 μm 0-80 mils	0-50 μm : 0.1 μm 50-2000 μm : 0.2 %	ø : 35 mm (1.4") min. ø : 18 mm (720 mils)	
	EGABI1.3-150 601-932	0-50 μm : 0.5 μm 50-1000 μm : 1 %	ø : 16 mm (630 mils) min. ø : 2 mm (80 mils)	
	0-1000 μm 0-40 mils	0-50 μm : 0.15 μm 50-1000 μm : 0.3 %	ø : 35 mm (1.4") min. ø : 9 mm (350 mils)	
Tquo; I	EGABI1.3-260 601-961	0-50 μm : 0.5 μm 50-1000 μm : 1 %	ø : 16 mm (630 mils) min. ø : 2 mm (80 mils)	
	0-1000 μm 0-40 mils	0-50 μm : 0.15 μm 50-1000 μm : 0.3 %	ø : 35 mm (1.4") min. ø : 9 mm (350 mils)	
	EGAB1.3-SD 602-107	0-50 μm : 0.5 μm 50-1000 μm : 1 % 1000-2000 μm : < 3 %	only for flat specimen	
	0-2000 μm 0-80 mils	0-100 μm : 0.5 μm 100-2000 μm : 0.5 %	only for flat specimen	
	V1EGA1HR34 602-109 V1EGA1HR34L 602-367	0-50 μm : 0.5 μm 50-1000 μm : 1 %	ø : 18 mm (700 mils) min. ø : 2 mm (80 mils)	
	0-1000 μm 0-40 mils	0-100 μm : 0.2 μm 100-1000 μm : 0.2 %	ø : 35 mm (1.4") min. ø : 7 mm (280 mils)	

magnetic induction measurement method



	 		
Ø for 10% error min. Ø	Probe tip radius	Height	
	Probe tip material	Diameter/width	Application
D for 10% error	replaceable probe tip	Length (see page 24	
ø : 8 mm (320 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)		Axial single tip probe with spring-loaded measuring system. Measures nonferrous- and nonmetal coatings on steel or iron
	Heat treated steel	10 mm (0.4")	substrate (NF, Iso/Fe). Especially well suited for coating thicknesses of ≤ 10 µm. The probe tip is subject to wear on hard and abrasive
D : 0.2 mm (8 mils)	yes	110 mm (4.3")	surfaces. The EGAB1.3 probe should be used for coating thicknesses > 100 μm.
ø : 8 mm (320 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)	23 mm (0.9")	Single tip right angle probe with spring-loaded measuring system. Measures nonferrous- and nonmetal coatings on steel or iron
	Heat treated steel	14 mm (0.6")	substrate (NF, Iso/Fe). Especially well suited for coating thicknesses of ≤ 10 µm (0.4 mil) in pipes, bore holes, recesses, etc.
D : 0.2 mm (8 mils)	yes	72 mm (2.8")	. The probe tip is subject to wear on hard and abrasive surfaces. The EGAWB1.3 probe should be used for coating thicknesses > 100 µm (4 mils).
ø : 8 mm (320 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)		Axial single tip probe with spring-loaded measuring system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Most commonly used probe for electroplated metal
	PVD coated	10 mm (0.4")	and organic coatings. For the measurement of nonferrous metal coatings on steel or iron. Scatter of the measuring values on rough
D : 0.2 mm (8 mils)	yes	110 mm (4.3"	(for example: grit blasted) surfaces is however relatively high. Double pole probes should be used in such instances if the geometry of the parts permits the use of this type of probe.
ø : 8 mm (320 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)	23 mm (0.9")	Single tip right angle probe with spring-loaded measuring system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Most commonly used probe for electro-
	PVD coated	14 mm (0.6")	plated metal and organic coatings in pipes, bore holes, recesses, etc. Scatter of the measuring values on rough (for example: grit
D : 0.2 mm (8 mils)	yes	72 mm (2.8")	blasted) surfaces is however relatively high. Double pole probes should be used in such instances if the geometry of the parts permits the use of this type of probe.
ø : 8 mm (320 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)	6.5 mm (0.26")	Single pole probe for inside measurement applications with spring- loaded measuring system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Suitable for mea-
	PVD coated	5.5 mm (0.22")	surements in bore holes, pipes or grooves. To obtain the smallest possible measurement uncertainty, externally triggered measure-
D : 0.2 mm (8 mils)	yes	320 mm (12.6")	ment acquisition should be used when measuring small inside diameters to prevent measurement errors. Smallest permissible inside diameter: 9 mm (0.36"). Maximum insertion depth: 150 mm (6").
ø : 8 mm (320 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)	6.5 mm (0.26")	Single pole probe for inside measurement applications with spring- loaded measuring system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Suitable for mea-
·	PVD coated	5.5 mm (0.22")	surements in bore holes, pipes or grooves. To obtain the smallest possible measurement uncertainty, externally triggered measure-
D : 0.2 mm (8 mils)	yes	430 mm (17")	ment acquisition should be used when measuring small inside diameters to prevent measurement errors. Smallest permissible inside diameter: 9 mm (0.36"). Maximum insertion depth: 260 mm (10").
ø : 8 mm (320 mils) min. ø : 8 mm (320 mils)	flat: ø 8 mm (320 mils)		Axial single tip probe with spring-loaded measuring system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). The flat surface probe tip is especially suited
	Polyamide	18 mm (0.7")	for soft coatings (screen printing material, soft plastic material, etc.). For the measurement of nonferrous metal coatings on steel
D : 0.2 mm (8 mils)	no	100 mm (4")	or iron. The surface to be measured has to be completely clean. Any foreign matter or dirt particles on the test surface produces measurement errors.
ø : 6 mm (240 mils) min. ø : 2 mm (80 mils)	0.8 mm (32 mils)	4.3 mm (0.17")	Single tip probe for inside measurement applications with fixed measurement system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Suitable for measurements in
	Tungsten carbide	4 mm (0.16")	bore holes, pipes or grooves. To obtain the smallest possible mea- surement uncertainty, externally triggered measurement acquisition
D : 0.2 mm (8 mils)	no	120 mm (4.7")	should be used when measuring small inside diameters to prevent measurement errors. Smallest permissible inside diameter: 7 mm (0.28"). Maximum insertion depth: 60 mm (2.4").

Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m. F: Measuring element protected against moist, aggressive media.	Description Order Number	Measurement accuracy* u _s	Measurement point # Ø for 10% error min. Ø
T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible. * Note: Probe capability (accuracy and precision) tested under controlled conditions.	Measurement range	Measurement precision* s	Ø for 10% error min. Ø
	EGA2H 602-121 EGA2HF 602-754	0-50 μm : 0.25 μm 50-500 μm : 0.5 % 500-1500 μm : < 1 %	ø : 25 mm (990 mils) min. ø : 2 mm (80 mils)
	0-1500 μm	0-50 µm : 0.15 µm	ø : 34 mm (1.3")
	0-60 mils	50-1500 µm : 0.3 %	min. ø : 22 mm (870 mils)
	EGAW2H 602-122	0-50 μm : 0.25 μm 50-500 μm : 0.5 % 500-1500 μm : < 1 %	ø : 25 mm (990 mils) min. ø : 2 mm (80 mils)
	0-1500 μm	0-50 μm : 0.15 μm	ø : 34 mm (1.3")
	0-60 mils	50-1500 μm : 0.3 %	min. ø : 18 mm (700 mils)
	EGB2 602-023	0-0,2 mm : 0.002 mm 0,2-3 mm : 1 % 3-5 mm : < 5 %	ø : 30 mm (1.2") min. ø : 2 mm (80 mils)
	0-5 mm	0-0,2 mm : 0.0005 mm	ø : 40 mm (1.6")
	0-200 mils	0,2-5 mm : 0.3 %	min. ø : 9 mm (350 mils)
	EGBW2 602-024	0-0,2 mm : 0.002 mm 0,2-3 mm : 1 % 3-5 mm : < 5 %	ø : 30 mm (1.2") min. ø : 2 mm (80 mils)
	0-5 mm	0-0,2 mm : 0.0005 mm	ø : 40 mm (1.6")
	0-200 mils	0,2-5 mm : 0.3 %	min. ø : 18 mm (700 mils)
	EK4	0-100 μm : 1 μm	ø : 22 mm (870 mils)
	602-123	100-2000 μm : 1 %	min. ø : 2 mm (80 mils)
	0-2000 μm	0-25 μm : 0.1 μm	ø : 38 mm (1.5")
	0-80 mils	25-2000 μm : 0.4 %	min. ø : 13 mm (510 mils)
	EKB4	0-100 μm : 0.5 μm	ø : 20 mm (800 mils)
	602-108	100-2000 μm : 0.5 %	min. ø : 2 mm (80 mils)
	0-2000 μm	0-50 μm : 0.15 μm	ø : 38 mm (1.5")
	0-80 mils	50-2000 μm : 0.3 %	min. ø : 13 mm (510 mils)
	V1EKB4	0-100 μm : 0.5 μm	ø : 20 mm (800 mils)
	602-126	100-2000 μm : 0.5 %	min. ø : 2 mm (80 mils)
	0-2000 μm	0-50 µm : 0.15 µm	ø : 38 mm (1.5")
	0-80 mils	50-2000 µm : 0.3 %	min. ø : 20 mm (800 mils)
	V7EK4 602-582	0-100 μm : 1.5 μm	ø : 22 mm (870 mils)
	V7EK4L 602-605	100-2000 μm : 1.5 %	min. ø : 2 mm (80 mils)
	0-2000 μm	0-25 μm : 0.1 μm	ø : 38 mm (1.5")
	0-80 mils	25-2000 μm : 0.4 %	min. ø : 20 mm (800 mils)

magnetic induction measurement method



			,
Ø for 10% error min. Ø	Probe tip radius	Height	
	Probe tip material	Diameter/width	Type of probe Application
D for 10% error	replaceable probe tip	Length (see page 24)	
ø : 15 mm (590 mils) min. ø : 2 mm (80 mils)	2.25 mm (88 mils)		Axial single tip probe with spring-loaded measuring system.
(00 11113)	Tungsten carbide	13 mm (0.5")	Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Due to the larger probe tip diameter better
ø : 15 mm (590 mils) min. ø : 2 mm (80 mils)	yes	80 mm (3.2")	suited for rough surfaces than the EGAB1.3 probe.
ø : 15 mm (590 mils) min. ø : 2 mm (80 mils)	2.25 mm (88 mils)	23 mm (0.9")	Axial single tip probe with spring-loaded measuring system.
	Tungsten carbide	14 mm (0.6")	Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Due to the larger probe tip diameter better
D : 0.4 mm (16 mils)	yes	72 mm (2.8")	suited for rough surfaces than the EGABW1.3 probe.
ø : 12 mm (470 mils) min. ø : 2 mm (80 mils)	1.0 mm (40 mils)		Axial single tip probe with spring-loaded measuring system.
	PVD coated	10 mm (0.4")	Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Has the largest measurement range of all single tip probes. Due to unshielded magnetic field larger
D : 0.25 mm (10 mils)	yes	110 mm (4.3")	geometric influence, however smaller tilting effect.
ø : 12 mm (470 mils) min. ø : 2 mm (80 mils)	1.0 mm (40 mils)	23 mm (0.9")	Single tip angle probe with spring-loaded measuring system.
	PVD coated	14 mm (0.6")	Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Same as EGB2 probe, however preferably
D : 0.25 mm (10 mils)	yes	72 mm (2.8")	used for measurements in pipes, bore holes or recesses.
ø : 30 mm (1.2") min. ø : 15 mm (590 mils)	1.25 mm (49 mils)	21 mm (0.8")	Double pole probe for angular measurements with fixed measurement system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Double pole probe producing
	Heat treated steel	12 mm (0.5")	the lowest possible measurement uncertainty. The uncoated probe tips make this probe especially suited for thin coatings (for
D : 0.4 mm (16 mils)	yes	18 mm (0.7")	example: lubricant and phosphate coatings). Greater measuring precision on rough surfaces than single tip probes, however faster probe tip wear than with EKB4 probe.
ø : 30 mm (1.2") min. ø : 15 mm (590 mils)	1.25 mm (49 mils)	21 mm (0.8")	Double pole probe for angular measurements with fixed measurement system. Measures ponferrous, and ponmetal coatings
(5555)	PVD coated	12 mm (0.5")	surement system. Measures nonferrous- and nonmetal coatings on steel or iron substrate (NF, Iso/Fe). Well suited for thin coatings. Higher measurement precision on rough surfaces than single
D : 0.4 mm (16 mils)	yes	18 mm (0.7")	pole probes.
ø : 30 mm (1.2") min. ø : 15 mm (590 mils)	1.25 mm (49 mils)		Double pole probe for inside measurements with spring-loaded measuring system. Measures nonferrous- and nonmetal coatings
	PVD coated	8.5 mm (0.3")	on steel or iron substrate (NF, Iso/Fe). Suitable for measurement in bore holes, pipes or grooves. Greater measuring precision on rough surfaces than with EGABI1.3-150 (260) probe.
D : 0.4 mm (16 mils)	yes	300 mm (11.8")	Smallest permissible inside diameter: 8.5 mm (0.34") Maximum insertion depth: 185 mm (7.4")
ø : 30 mm (1.2") min. ø : 15 mm (590 mils)	1.25 mm (49 mils)		Axial double-tip measurement probe with spring-loaded measuring element. Measures nonferrous and nonmetal coatings on steel or iron (NE, Iso/Fe). Especially well suited for thin layers (phosphorous
	Heat treated steel	20 mm (0.8")	coatings) because of uncoated probe tips. Higher repeatability than single tip probes when measuring rough surfaces. Spring
D : 0.4 mm (16 mils)	yes	70 mm (2.8")	loaded measuring system allows exact positioning and constant pressure force, which is advantageous for measuring weak coatings.

Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m.	Description Order Number	Measurement accuracy* u _s	Measurement point Ø for 10% error min. Ø	
F: Measuring element protected against moist, aggressive media. T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible. * Note: Probe capability (accuracy and precision) tested under controlled conditions.	Measurement range	Measurement precision* s	Ø for 10% error min. Ø	
	V7EKB4 602-583	0-100 μm : 1 μm	ø : 20 mm (800 mils)	
	V7EKB4L 602-606	100-2000 μm : 1 %	min. ø : 2 mm (80 mils)	
	0-2000 μm	0-50 μm : 0.15 μm	ø : 38 mm (1.5")	
	0-80 mils	50-2000 μm : 0.3 %	min. ø : 20 mm (800 mils)	
	EKB10	0-0.5 mm : 0.005 mm	ø : 50 mm (2")	
	602-225	0.5-8 mm : 1 %	min. ø : 2 mm (80 mils)	
	0-8 mm	0-0.5 mm : 0.0025 mm	ø : 75 mm (3")	
	0-320 mils	0.5-8 mm : 0.5 %	min. ø : 24 mm (950 mils)	
	EKB10-OD 602-165	0-0.5 mm : 0.005 mm	ø : 50 mm (2")	
	EKB10L-OD 602-760	0.5-8 mm : 1 %	min. ø : 2 mm (80 mils)	
	0-8 mm	0-0.5 mm : 0.0015 mm	∞	
	0-320 mils	0.5-8 mm : 0.3 %	∞	
	V1EKB10	0-0.5 mm : 0.01 mm	ø : 50 mm (2")	
	602-676	0.5-8 mm : 2 %	min. ø : 2 mm (80 mils)	
	0-8 mm	0-0.5 mm : 0.0025 mm	ø : 75 mm (3")	
	0-320 mils	0.5-8 mm : 0.5 %	min. ø : 24 mm (950 mils)	
-fiecher	EKB25 601-952 EKB25L 602-913	0-1 mm : 0.02 mm 1-7 mm : 2 % 7-15 mm : < 5 %	ø : 60 mm (2.4") min. ø : 10 mm (400 mils)	
	0-15 mm 0-590 mils	0-0.5 mm : 0.01 mm 0.5-15 mm : 2 %	ø : 85 mm (3.3") min. ø : 20 mm (800 mils)	

Note concerning the application of probes using the magnetic induction measurement method:

Please consult with the manufacturer before measuring electrically conducting coatings with thicknesses > 500 µm (20 mils).

magnetic induction measurement method



Ø for 10% error min. Ø	Probe tip radius Probe tip material	Height Diameter/width	Type of probe
D for 10% error	replaceable probe tip	Length (see page 24)	Application -
ø : 30 mm (1.2") min. ø : 15 mm (590 mils)	1.25 mm (49 mils)		Axial double tip measurement probe with spring-loaded measuring system. Measurement of nonferrous- and nonmetal coatings on
	- PVD coated	20 mm (0.8")	steel or iron substrate (NF, Iso/Fe). Higher measurement precision on rough surfaces than single tip probes. Spring-loaded measuring system provides better positioning and constant pressure force (advantageous for
D : 0.4 mm (16 mils)	yes	70 mm (2.8")	measuring soft coatings).
ø : 30 mm (1.2") min. ø : 20 mm (800 mils)	1.5 mm (60 mils)	27 mm (1.1")	
	- PVD coated	14 mm (0.5")	Double pole probe for angular measurements with fixed measurement system. Especially well suited for thick coatings. Greater measuring precision on rough surfaces than single pole probes.
D : 0.5 mm (20 mils)	yes	50 mm (2")	
ø : 30 mm (1.2") min. ø : 38 mm (1.5")	flat: 34 x 24 mm (1300 x 950 mils)	26 mm (1.0")	
	Polyamide	24 mm (1.0")	Double pole probe for angular measurements with fixed measurement system. The large flat contact surface is especially well suited for thick and compressible soft coatings (for example rubber sheeting for offset
D : 0.5 mm (20 mils)	no	53 mm (2.1")	. printing).
ø : 30 mm (1.2") min. ø : 20 mm (800 mils)	1.5 mm (60 mils)		Double pole probe for angular measurements with spring-loaded measuring system.
	- PVD coated	13 mm (0.5")	Suitable for thick coatings in bore holes, pipes, or recesses. Greater measuring precision on rough surfaces than with single pole probes. Externally triggered measurement acquisition should be used with small inside diameters to prevent measurement errors.
D : 0.5 mm (20 mils)	yes	380 mm (15")	Smallest permissible inside diameter: 13 mm (0.5") Maximum insertion depth : 260 mm (10")
ø : 50 mm (2") min. ø : 40 mm (1.6")	1.5 mm (60 mils)	33 mm (1.3")	
	- PVD coated	20 mm (0.8")	Double pole probe for angular measurements with fixed measurement system. Especially suited for thick, nonmetallic coatings.
D : 0.7 mm (28 mils)	yes	65 mm (2.6")	

Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m. F: Measuring element protected against moist,	Description Order Number	Measurement accuracy* u _s	Measurement point Ø for 10% error min. Ø
aggressive media. T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible.	Measurement	Measurement precision*	Ø for 10% error
* Note: Probe capability (accuracy and precision) tested under controlled conditions.	range	s	min. Ø
[+ischer=	EK50 602-127 EK50L 602-923	0-1 mm : 0.05 mm 1-10 mm : 5 % 10-30 mm : < 7 %	ø : 100 mm (4") min. ø : 10 mm (400 mils)
	0-30 mm 0-1200 mils	0-1 mm : 0.02 mm 1-30 mm : 2%	ø : 140 mm (5.5") min. ø : 14 mm (550 mils)
	EGA06H 602-936 EGA06H-L 602-626	0-50 μm : 0.3 μm 50-700 μm : < 2 %	ø : 18 mm (720 mils) min. ø : 1 mm (40 mils)
	0-700 μm 0-28 mils	0-50 μm : 0.1 μm 50-700 μm : < 0.3 %	ø : 30 mm (1.2") min. ø : 20 mm (800 mils)
	EGA06H-MC 603-092	0-70 μm : 0.3 μm 70-700 μm : < 2 %	ø : 18 mm (720 mils) min. ø : 1 mm (40 mils)
	0-700 μm 0-28 mils	0-70 μm : 0.08 μm 70-700 μm : < 0.08 %	ø : 30 mm (1.2") min. ø : 20 mm (800 mils)
	V2EGA06H 603-112	0-50 μm : 0.3 μm 50-700 μm : < 2 %	ø : 18 mm (720 mils) min. ø : 1 mm (40 mils)
	0-700 μm 0-28 mils	0-50 μm : 0.1 μm 50-700 μm : < 0.3 %	

eddy current measuring method



Ø for 10% error min. Ø	Probe tip radius	Height	
	Probe tip material	Diameter/width	Type of probe Application
D for 10% error	replaceable probe tip	Length (see page 24)	
ø : 84 mm (3.3") min. ø : 70 mm (2.8")	2.5 mm (98 mils)	33 mm (1.3")	Double pole probe for angular measurements with fixed
	Heat treated steel	20 mm (0.8")	measurement system. Especially suited for very thick, nonmetallic coatings. For austenitic stainless steel coatings smaller measurement errors due to ferromagnetic delta ferrite content than with all other types of probes.
D : 1.2 mm (47 mils)	yes	95 mm (3.7")	of probes.
ø: 5 mm (200 mils) min. ø: 2 mm (80 mils)	0.3 mm (12 mils)	110 mm (4.4")	Axial single tip measurement probe with spring-loaded measuring
	Tungsten carbide	13 mm (0.52")	system. Measures electrically nonconducting or nonferrous coatings on steel or iron (NF/Fe). Mechanical design especially suited for installation in customerspecific probe fixtures or guide devices for precise probe
D : 0.25 mm (10 mils)	no		positioning.
ø: 5 mm (200 mils) min. ø: 2 mm (80 mils)	0.3 mm (12 mils)	110 mm (4.4")	Axial single tip measurement probe with spring-loaded measuringt
	Tungsten carbide	13 mm (0.52")	system. Measures electrically nonconducting or nonferrous coatings on steel or iron (NF/Fe). Mechanical design especially suited for installation in customer-specific probe fixtures or guide devices for precise probe
D : 0.25 mm (10 mils)	no		positioning.
ø: 5 mm (200 mils) min. ø: 2 mm (80 mils)	0.3 mm (12 mils)		Measures electrically nonconducting or nonferrous metal coatings on steel or iron (NF/Fe). Measuring element same as
	Tungsten carbide	10 mm (0.4")	with EGA06H probe. Especially well suited for the integration in automated measurement systems. No measurement tip wear even after several million measurement cycles when used properly.
D : 0.25 mm (10 mils)	no	110 mm (4.4")	Suited for cylindrical specimen with diameter range 8 to 25 mm. (0.32" to 1"). Other diameters on request.

Note regarding probe designations:		Measurement	Measurement point	
L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m.	Description Order Number	accuracy*	Ø for 10% error min. Ø	
F: Measuring element protected against moist, aggressive media.				
T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible.	Measurement	Measurement precision*	Ø for 10% error	
* Note: Probe capability (accuracy and precision) tested under controlled conditions.	range	s	min. Ø	
	ETA3.3H 602-128 ETA3.3HL 602-799	0-50 μm : 0.25 μm 50-800 μm : 0.5 %	ø : 50 mm (2") min. ø : 2 mm (80 mils)	
		800-1200 μm : < 2 %		
	0-1200 μm 0-45 mils	0-50 μm : 0.15 μm 50-1200 μm : 0.3 %	ø : 50 mm (2") min. ø : 30 mm (1.2")	
	ETA3.3	0-100 μm : 0.5 μm 100-800 μm : 0.5 %	ø : 50 mm (2")	
	601-797	800-1200 µm : < 3 %	min. ø: 2 mm (80 mils)	
	0-1200 μm 0-45 mils	0-100 μm : 0.2 μm 100-1200 μm : 0.2 %	ø : 55 mm (2.2") min. ø : 30 mm (1.2")	
B. C.			/	
	ETA3.3FG 602-623	0-50 μm : 0.25 μm 50-1200 μm : 0.5 %	ø : 50 mm (2") min. ø : 2 mm (80 mils)	
	0-1200 μm 0-45 mils	0-50 μm : 0.1 μm 50-1200 μm : 0.2 %	∞ ∞	
	0-45 mils	<u> </u>		
-11714-	ETA3.3-5.6 602-645	0-100 μm : 0.5 μm 100-800 μm : 0.5 % 800-1200 μm : < 3 %	ø : 50 mm (2") min. ø : 2 mm (80 mils)	
	0-1200 μm 0-45 mils	0-100 μm : 0.2 μm 100-1200 μm : 0.2 %	ø : 50 mm (2") min. ø : 30 mm (1.2")	
	EAW3.3 602-025 EAW3.3L 602-922	0-50 μm : 0.75 μm 50-1200 μm : 1.5 %	ø : 50 mm (2") min. ø : 2 mm (80 mils)	
	0-1200 μm 0-45 mils	0-50 μm : 0.25 μm 50-1200 μm : 0.5 %	ø : 50 mm (2") min. ø : 34 mm (1.6")	
	EAI3.3-150 602-026	0-200 μm : 1 μm 200-800 μm : 0.5 %	ø : 60 mm (2.4") min. ø : 2 mm (80 mils)	
	0-800 μm 0-32 mils	0-100 μm : 0.3 μm 100-800 μm : 0.3 %	ø : 55 mm (2.2") min. ø : 9 mm (350 mils)	
	EA9 601-965	0-0.25 mm : 0.005 mm 0.25-2.5 mm : 2 % 2.5-3.5 mm : < 3.5 %	ø : 160 mm (6.3") min. ø : 2 mm (80 mils)	
	0-3.5 mm 0-140 mils	0-1 mm : 0.002 mm 1-3.5 mm : 0.2 %	ø : 160 mm (6.3") min. ø : 40 mm (1.6")	
	EA30 602-027 EA30L 602-633	0-2 mm : 0.05 mm 2-20 mm : 2.5 %	ø : 1200 mm (47") min. ø : 200 mm (7.9")	
	0-20 mm 0-800 mils	0-1 mm : 0.002 mm 1-20 mm : 0.2 %	∞ ∞	

eddy current measuring method



Ø for 10% error min. Ø	Probe tip radius	Height	 Type of probe
	Probe tip material	Diameter/width	Application
D for 10% error	replaceable probe tip	Length (see page 24)	
ø: 4 mm (160 mils) min. ø: 2 mm (80 mils)	1.2 mm (47 mils)		Axial single tip probe with spring-loaded measuring system. Measurement of nonconductive coatings on nonferromagnetic substrate (Iso/NF).
	Tungsten carbide	18 mm (0.7")	Highly impact- and shatter resistant probe tip. Standard probe for paint and plastic coatings. Should not be used
D : 0.09 mm (3.5 mils)	yes	70 mm (2.8")	when surfaces exhibit a damp condition (acidic contamination of test surface).
ø: 4 mm (160 mils) min. ø: 2 mm (80 mils)	1.2 mm (47 mils)		Axial single tip probe with spring-loaded measuring system. Measurement of nonconductive coatings on nonferromagnetic
(00 11113)	Jewel tip	18 mm (0.7")	substrate (lso/NF). Standard probe for paint and plastic coatings, as well as for
D : 0.09 mm (3.5 mils)	yes	70 mm (2.8")	anodized coatings. Can possibly also be used when surfaces exhibit a damp condition (acidic contamination of test surface). Smaller tilting effect than with ETA3.3F probe.
ø : 15 mm (590 mils) min. ø : 7 mm (280 mils)	2.5 mm (98 mils)		Axial single tip probe with spring-loaded measuring system. Measurement of nonconductive coatings on nonferromagnetic
	Polyamide	18 mm (0.7")	substrate (Iso/NF). Especially suited for anodized coatings when surfaces exhibit a
D : 0.09 mm (3.5 mils)	yes	70 mm (2.8")	wet (acidic) contamination of the test surface. Larger tilting effect than with ETA3.3 probe.
ø: 4 mm (160 mils) min. ø: 2 mm (80 mils)	2.8 mm (110 mils)		Axial single tip probe with spring-loaded measuring system. Measurement of nonconductive coatings on nonferromagnetic
	Jewel tip	18 mm (0.7")	substrate (Iso/NF). Due to the larger radius of the probe tip lower measurement
D : 0.09 mm (3.5 mils)	yes	70 mm (2.8")	scatter on rough surfaces than with ETA3.3 probe.
ø: 4 mm (160 mils) min. ø: 2 mm (80 mils)	1.2 mm (47 mils)	23 mm (0.9")	Single tip angle probe with spring-loaded measuring system. Measurement of nonconductive coatings on nonferromagnetic
	Jewel tip	14 mm (0.6")	substrate (Iso/NF). Suitable for measurements on flat objects or in pipes, bore holes
D : 0.09 mm (3.5 mils)	yes	72 mm (2.8")	and recesses. Can also be used when surfaces exhibit a damp condition (acidic contamination of test surface).
ø: 4 mm (160 mils) min. ø: 2 mm (80 mils)	1.2 mm (47 mils)	6.5 mm (0.26")	Single tip angle probe with spring-loaded measuring system. Measurement of nonconductive coatings on nonferromagnetic
2 . 2 (00	Jewel tip	5.5 mm (0.22")	substrate (Iso/NF). Suitable for measurements in pipes, bore holes and recesses, etc.
D : 0.09 mm (3.5 mils)	yes	320 mm (12.6")	Can possibly also be used when surfaces exhibit a wet condition (acidic contamination of test surface). To avoid positioning errors externally triggered measurement acquisition should be used.
ø: 4 mm (160 mils) min. ø: 2 mm (80 mils)	8 mm (320 mils)	23 mm (0.9")	Single tip angle probe with spring-loaded measuring system.
ווווו (ou iiilis) . ב . ב . iiiii	Heat treated steel	14 mm (0.6")	Measurement of nonconductive coatings on nonferromagnetic substrate (lso/NF).
D : 0.09 mm (3.5 mils)	no	72 mm (2.8")	Suitable for measurement of thicker plastic- or rubber coatings.
ø : 42 mm (1.6") min. ø : 34 mm (1.3")	flat: ø 34 mm (1.3")	43 mm (1.7")	Single tip angle probe with fixed measurement systems. Measurement of nonconductive coatings on nonferromagnetic substrate (Iso/NF).
	Polyamide	34 mm (1.3")	Suitable for measurement of thicker plastic- or rubber coatings. Also to measure wall thickness of, for example, plastic tanks with
D : 0.09 mm (3.5 mils)	no	60 mm (2.4")	an aluminum backing foil. For surfaces with larger curvature a V-groove adapter shoe has to be used.

Note regarding probe designations:			Measurement point	
L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m.	Description Order Number	Measurement accuracy* u _s	Ø for 10% error min. Ø	
F: Measuring element protected against moist, aggressive media.				
T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible.	Measurement	Measurement precision*	Ø für 10%-Fehler min. Ø	
* Note: Probe capability (accuracy and precision) tested under controlled conditions.	range	s		
	EA70 602-028	0 - 5 mm : 0.05 mm 5 - 50 mm : 1 %	ø : 2500 mm (98") min. ø : 300 mm (11.9")	
	0 - 50 mm 0 - 2"	0 - 50 mm : 0.3 %	∞ ∞	
	ETA3.3-Cu** 602-550	0 - 10 μm : 0.3 μm	ø : 50 mm (2")	
	ETA3.3F-Cu** 603-015	10 - 130 µm : 3 %	min. ø : 1 mm (40 mils)	
	0 - 150 μm 0 - 6 mils Cu/Iso	0 - 20 μm : 0.2 μm 20 - 130 μm : 1 %	ø : 55 mm (2.2") min. ø : 10 mm (400 mils)	
	ETA3.3-CuMR1** 603-161	0.5 - 15 μm : 0.3 μm		
-	0.5 - 15 μm 0.02 - 0.6 mil	0.5 - 8 µm : 0.1 µm 8 - 15 µm : 1.2 %		
	ETA3.3-CuMR2** 603-164	2 - 10 μm : 0.1 μm 10 - 50 μm : 1 %		
	2 - 50 µт 0.08 - 2 mils	2 - 10 µm : 0.05 µm 10 - 50 µm : 0.5 %		
	ETA3.3-CuMR3** 603-167	10 - 100 μm : 1.5 μm 100 - 250 μm : 1.5 %		
	10 - 250 μm 0.4 - 10 mils	10 - 100 µm : 0.5 µm 100 - 250 µm : 0.5 %		
	ETA3.3-Cr** 602-607	0 - 50 μm : 1 μm 50 - 500 μm : 2 %	ø : 50 mm (2") min. ø : 1 mm (40 mils)	
- C - KASAMAN	0 - 500 μm 0 - 20 mils Cr/NF	0 - 50 μm : 0.5 μm 50 - 500 μm : 1 %	ø : 55 mm (2.2") min. ø : 10 mm (400 mils)	
	ETD3.3 602-607	0 - 100 μm : 1 μm 100 - 800 μm : 1 %	ø : 4 mm (160 mils) min. ø : 2 mm (80 mils)	
	0 - 800 μm 0 - 32 mils	0 - 100 μm : 0.2 μm 100 - 800 μm : 0.2 %	ø : < 40 mm (1.6") min. ø : 40 mm (1.6")	
	ET280** 602-302	0 - 10 cm : 0.05 cm 10 - 30 cm : 0.5 %		
	1 - 30 cm 0.4 - 12"	0 - 10 cm : 0.01 cm 10 - 30 cm : 0.1 %		

^{**} Probe can not be connected to FISCHERSCOPE® MMS®

eddy current measuring method



	,		
Ø for 10% error min. Ø	Probe tip radius	Height Diameter/width	Type of probe
	Probe tip material	Diameter/width	Application
D for 10% error	replaceable probe tip	Length (see page 24)	
ø : 82 mm (3.2") min. ø : 74 mm (2.9")	flat: ø 75 mm (3")	43 mm (1.9")	Single tip angle probe with fixed measurement systems. Measurement of nonconductive coatings on nonferromagnetic
	- Polyamide	75 mm (3")	substrate (Iso/NF). Suitable for measurements of very thick plastic- or rubber coatings, however mainly to measure wall thickness of, for
D : 0.09 mm (3.5 mils)	no	80 mm (3.1")	example, plastic tanks with an aluminum backing foil. For surfaces with larger curvature a V-groove adapter shoe has to be used.
ø : 4 mm (160 mils)	1.2 mm (48 mils)		Axial single tip measurement probe with spring-loaded
min. ø : 2 mm (80 mils)	Jewel tip	10 mm (0.4")	measuring system. Measures nonferrous- and nonmetal coatings on electrically nonconducting substrate (NF/Iso). Preferred application is copper thickness measurement on
no substrate influence	yes	110 mm (4.4")	pc-board surfaces. The copper may not be lacquered.
ø : 2 mm (80 mils)	1.2 mm (48 mils)	70 mm (2.8")	Axial single tip measurement probe with spring-loaded measuring system.
board thickness (Epoxy)	Jewel tip	18 mm (0.7")	Measures nonferrous metal coatings on nonferromagnetic substrate (ISO/NE). Especially well suited for measuring Cu coating thickness on pc-boards. The copper may not be
0.4 mm (16 mils)	yes		laquered.
ø : 2 mm (80 mils)	1.2 mm (48 mils)	70 mm (2.8")	Axial single tip measurement probe with spring-loaded measuring
board thickness (Epoxy)	- Jewel tip	18 mm (0.7")	system. Same applications as ETA3.3-CuMR1 probe, however suitable for thicker coatings.
0.8 mm (32 mils)	yes		
ø : 2 mm (80 mils)	1.2 mm (48 mils)	110 mm (4.4")	Axial single tip measurement probe with spring-loaded measuring
board thickness (Epoxy)	Jewel tip	10 mm (0.4")	system. Same applications as ETA3.3-CuMR1 and -MR2 probes, however suitable for thicker coatings.
1 mm (40 mils)	yes		
ø : 4 mm (160 mils) min. ø : 2 mm (80 mils)	1.2 mm (48 mils)		Axial single tip measurement probe with spring-loaded measuring system.
	Jewel tip	10 mm (0.4")	Measures chrome coatings on nonferrous substrate like steel, aluminum or copper. Measuring of chrome coatings on stainless steel or titanium or
D : 0.7 mm (28 mils) (Al)	yes	110 mm (4.4")	other subtrates with very low electrical conductivity is not possible.
ø : 6 mm (240 mils) min. ø : 3 mm (120 mils)	1.2 mm (48 mils)		Patented axial single tip measurement probe with spring-loaded measuring system. Unique curvature compensation for measuring paint-, laquer-,
	Jewel tip	16 mm (0.6")	plastic and anotized coatings on nonferrous metals. Especially well suited for curved surfaces like motorcar body sheet, blinds etc.
D : 0.09 mm (3.6 mils)	yes	70 mm (2.8")	Probe can be operated with Fischer instrument types DUALSCOPE® MP20 or MP40.
		205 mm (8.2")	Axial measurement probe with fixed measurement system. Measures nonmetal coatings on nonferromagnetic substrate materials (Iso/NF) or on steel and iron (Iso/Fe).
		300 mm (12")	Suited for measurements of the pavement thickness in road construction, thick synthetic or rubber coatings or for measuring
	no		the thickness of walls of, e.g., large-volume synthetic tanks by placing an aluminum foil on the other side.

Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m. F: Measuring element protected against moist, aggressive media.	Description Order Number	Measurement accuracy* u _s	Measurement point Ø for 10% error min. Ø	
T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible. * Note: Probe capability (accuracy and precision) tested under controlled conditions.	Measurement range	Measurement precision* s	Ø for 10% error min. Ø	
	EDX10 603-084	NF/Fe Zn 15-30 μm (0.6-1.2 mils): 15 % Zn ≥ 30 μm (1.2 mils): 5 % Iso/NF Paint 0-50 μm (2 mils): 5 % Paint ≥ 50 μm (2 mils): 1 %	ø: 13 mm (520 mils) (NF/Fe) min. ø: 1 mm (40 mils) (NF/Fe) ø: 45 mm (1.8") (Iso/NF) min. ø: 1 mm (40 mils) (Iso/NF)	
	0 - 800 μm (32 mils) Total paint + Zn (NF/Fe) or only paint (paint/Fe)	NF/Fe Zn 15-30 μm (0.6-1.2 mils) : 0.6 μm Zn ≥ 30 μm (1.2 mils) : 2 % Iso/Fe Paint ≤ 1.5 μm (0.06 mil)	ø : 30 mm (1.2") (NF/Fe) min. ø : 15 mm (600 mils) (NF/Fe) ø : 45 mm (1.8") (Iso/Fe) min. ø : 15 mm (600 mils) (Iso/Fe)	
	ED10 602-796 ED10L 602-093	NF/Fe 0-50 μm : 0.2 μm (0.008 mil) 50-1500 μm (0-60 mils) : 1 % Iso/NF 0-100 μm : 0.5 μm (0.02 mil) 100-1200 μm (4-48 mils) : 0.5 %	ø : 15 mm (600 mils) (NF/Fe) min. ø : 1 mm (40 mils) (NF/Fe) ø : 75 mm (3") (Iso/NF) min. ø : 1 mm (40 mils) (Iso/NF)	
	Dual Mode 0-800 μm (0-32 mils) (NE/Fe) 0-800 μm (0-32 mils) (Iso/NE) Single Mode 0-1500 μm (0-60 mils) (NE/Fe) 0-1200 μm (0-48 mils) (Iso/Fe)	NF/Fe 0-50 μm : 0.1 μm (0.004 mil) 50-1500 μm (2-60 mils) : 0.5 % Iso/NF 0-100 μm : 0.2 μm (0.008 mil) 100-1200 μm : 0.5 %	ø : 30 mm (1.2") (NF/Fe) min. ø : 15 mm (600 mils) (NF/Fe) ø : 75 mm (3") (lso/NF) min. ø : 15 mm (600 mils) (lso/NF)	

Note: Electrical conductivity changes of the base material in the range between 17 MS/m and 58 MS/m (30-100% IACS) cause

Characteristic values and technical data of probes for the

Description/No.	u _s *	Lift-off h Convex curvature
ESD1 ⁽¹⁾ 602-307 ESD1L ⁽¹⁾ 602-898	0-500 μm (0-20 mils) (Zn/Fe) 0-180 μm (0-7.2 mils) (Cu/Fe) 0-100 μm (0-4 mils) (Ni/Fe) 0.04 μm (0.0016 mils) or 1 % (Zn/Fe)	h : 0-700 μm (0-28 mils) (NF/Fe) h : 0-200 μm (0-8 mils) (Ni/Fe) Ø 10%: 4 mm/2 mm (160/80 mils) at 25 μm (1 mil) Zn/Fe
	0.1 μm (0.004 mils) or 2 % Ni/Fe)	min ø: 4 mm/2 mm (160 mils/80 mils) at 25 μm (1 mil) Ni/Fe
	0-200 μm (0-8 mils) (Zn/Fe) 0-80 μm 80-3.2 mils) (Cu/Fe)	h : 0-700 μm (0-28 mils) (NF/Fe)
ESD2 602-308	0-50 μm (0-2 mils) (Ni/Fe) 0.02 μm (0.008 mils) or 0.5 % (Zn/Fe) 0.05 μm (0.002 mils) or 1 % (Ni/Fe)	h : 0-200 μm (0-8 mils) (Ni/Fe) Ø 10%: 4 mm/2 mm (160/80 mils) at 25 μm (1 mil) Zn/Fe min Ø: 4 mm/2 mm (160 mils/80 mils) at 25 μm (1 mil) Ni/Fe

Index description see page 22.

eddy current measuring method

Ø for 10% error min. Ø	Probe tip radius	Height	
	Probe tip material	Diameter/width	Type of probe Application
D for 10% error	replaceable probe tip	Length	
		(see page 24)	
NF/Fe Edge effect: 0.5 mm (20 mils) Min. ø : 2 mm (28 mils) Iso/Fe	0.75 mm (30 mils)		Axial measurement probe for simultaneous measurement of
Edge effect: 0.7 mm Min. ø : 2 mm (28 mils)	Tungsten carbide	13 mm (0.5")	individual coating thicknesses of duplex coatings (paint/zinc) on steel sheets (e.g., in household appliance manufacturing) or on steel constructions in structural metal engineering. Both electro-galvanized and hot galvanized coatings can be measured.
NF/Fe ø: 0.4 mm (16 mils) Iso/Fe depending on the normalization layer	no	100 mm (4")	Probe can be connected to measuring instrument models DUALSCOPE® MP20 and MP40.
ø :12 mm (480 mils) (NF/Fe) min. ø : 2 mm (80 mils) (NF/Fe)	0.75 mm (30 mils)		Axial measurement probe for simultaneous measurement of individual coating thicknesses according to the magnetic induction method and eddy current method. Especially well suited for measuring paint- and laquer thicknesses
ø : 4 mm (160 mils) (Iso/NF) min. ø : 2 mm (80 mils) (Iso/NF)	- Tungsten carbide	on stee probe t surface Both el	on steel or iron or aluminum or copper etc. Because of small probe tip not suited for measuring on rough e.g. shot-blasted surfaces. Both electro-galvanized and hot galvanized coatings can be measured.
D : 0.2 mm (8 mils) (NF/Fe) D : 0.09 mm (4 mils) (Iso/NF)	no	100 mm (4")	Probe can be connected to instrument models DUALSCOPE® MP10/20/30/40 (depending on the measuring method) and FISCHERSCOPE® MMS® module PERMASCOPE®.

a measurement error of < 2% with all eddy current probes listed in the tables.

phase-sensitive eddy current measurement method

Ø for 10% error D for 10% error	Probe tip radius Probe tip material replaceable probe tip	Height <i>Diameter/width</i> Length (see page 24)	Type of probe Application
6 mm/4 mm (240/160 mils) at 25 µm (1 mil) Zn/Fe 6 mm/4 mm (240/160 mils) at 25 µm (1 mil) Ni/Fe	flat: ø 5.5 mm (220 mils)		Measurement of nonferrous metal coatings on steel and iron (NF/Fe) or nonferrous metal coatings on nonferrous substrates (NF/NF), as well as electroplated nickel coatings on steel (Ni/Fe). Suited especially for fast, non-destructive measurement of nickel coatings. Produces very little measurement scatter when mea-
0.1 mm (4 mils)	Polyamide	16 mm (0.6")	suring NF-coatings on very rough steel surfaces. Measurement of NF-coatings on NF-substrate if the electrical conductivity of the coating material is at least double the conductivity of the substrate
0.1 mm (4 mils)	no	110 mm (4.3")	material. Due to lift-off compensation of the test signal it is possible to perform noncontacting measurements or measurements of coatings under a nonconductive coating up to 700 μm (28 mils) (for Ni up to 200 μm (8 mils)) thickness. The measurement system is moisture proof.
6 mm/2 mm (240/80 mils) at 25 μm (1 mil) Zn/Fe	flat: ø 5.5 mm (220 mils)		Axial single tip measurement probe with spring-loaded measuring element.
6 mm/2 mm (240/80 mils) at 25 µm (1 mil) Ni/Fe	Polyamide	16 mm (0.6")	Measures nonferrous metal coatings on steel or iron (NF/Fe) or on nonferrous metal coatings (NF/NF) and galvanized nickel coatings
0.1 mm (4 mils)			on steel or iron (Ni/Fe). Same applications and characteristics as ESD1 probe, however
0.1 mm (4 mils)	no	110 mm (4.3")	suitable for thinner coatings. As with probes ESD1 and ESD3 very little influence from test area geometry.

Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m. F: Measuring element protected against moist,	Description	Measurement range	Probe the Lift-off h Coating
aggressive media. T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible. * Note: Probe capability (accuracy and precision) tested under controlled conditions.	Order Number	Measurement precision* s (the greater value applies)	Measurement point Ø for 10% error/min. Ø
	ESD3 ⁽¹⁾	0 - 2000 μm (Zn/Fe) 0 - 1000 μm (Cu/Fe)	0 - 700 μm (28 mils)
	602-309	0.2 μm or 0.5 % (Cu/Fe)	22 mm/6 mm (870/240 mils) at 200 μm (8 mils) Cu/Fe
403000	ESL08A ⁽¹⁾	5 - 80 μm (Cu/lso)	Lift-off compensation for bore diameters of 0.8 - 1.8 mm (32 to 70 mils)
	602-224	0.3 μm or 1 %	only for measurements in boreholes with 0.8 to 2.0 mm (32 to 80 mils) diameter
	SL08A [®]	5 - 80 μm (Cu/lso)	Lift-off compensation for bore diameters of 0.8 - 1.8 mm (32 to 70 mils)
The state of the s	602-385	0.3 μm or 1 %	only for measurements in boreholes with 0.8 to 2.0 mm (32 to 80 mils) diameter
	ESG2 ⁽⁷⁾ 602-311	1 - 800 μm (paint/Zn) 1 - 100 μm (Zn/Fe)	no lift-off compensation
	ESG2L® 602-724	1 μm or 1 % (paint/Zn) 1 μm or 1 % (Zn/Fe)	ø : 20 mm (800 mils) (paint/Zn) ø : 6 mm (240 mils) (Zn/Fe)
	ESC1(1)	0 - 170 μm (Cu/lso) 0 - 700 μm (Cr/Cu)	h : 0 - 300 µm (12 mils) no lift-off compensation
	602-658	0.04 μm or 1 % (Cu/lso) 0.1 μm or 2 % (Cr/Cu)	6 mm/3 mm (240/120 mils) at 100 μm (4 mils) Cu/lso 35 mm/2 mm (1400/80 mils) at 230 μm (9 mils) Cr/Al
	ESC2	0 - 90 μm (Cu/lso) 0 - 200 μm (Cr/Cu)	h : 0 - 300 µm (12 mils) no lift-off compensation
	602-237	0.02 μm or 0.5 % (Cu/lso) 0.05 μm or 1 % (Cr/Cu)	6 mm/3 mm (240/120 mils) 35 mm/2 mm (1400/80 mils) at 150 μm (6 mils) Cr/Al
	ESC3 ⁽¹⁾	90 - 1000 μm (Cu/lso)	0 - 500 μm (0 - 20 mils)
	603-039	0.3 μm/0.5 %	not relevant

Index description see page 22.

sensitive eddy current measurement method




Ø for 10% error/min. Ø	Probe tip radius Probe tip material	Height Diameter/width	Type of probe
D for 10% error	replaceable probe tip	Length (see page 24)	Application -
15 mm/10 mm (0.6/0.4") at 200 μm (8 mils) Cu/Fe	flat: ø 15 mm (600 mils)		Measures nonferrous metal coatings on steel or iron (NF/Fe) or
0.2 mm (8 mils)	Polyamide	35 mm (1.4") 	nonferrous metal coatings (NF/NF). Same applications (except Ni/Fe) and characteristics as ESD1 probe, however suitable for thicker coatings.
0.2 mm (0 mms)	no	130 mm (5.2")	
not relevant	ø Probe tip: 0.78 mm (31 mils)		Single tip axial probe for inside measurements with fixed measurement system.
board thickness from D = 0.5 mm	Austenitic steel	13 mm (0.5")	Designed specifically to measure the thickness of copper plating (even under a Sn- or SnPb-coating) in metallized through holes of PC-boards. Smallest permissible PTH diameter: 0.8 mm
(20 mils) to 2.5 mm (100 mils) can be entered	no	100 mm (4")	(32 mils).
not relevant	ø Probe tip: 0.78 mm (31 mils)		Single pole probe for inside measurements with fixed
board thickness from D = 0.5 mm	Austenitic steel	13 mm (0.5")	measurement system. Same as ESL08A probe, however used only for CU-SCOPE CMP1A.
(20 mils) to 2.5 mm (100 mils) can be entered	no	100 mm (4")	So cool E GWI W.
10 mm/4 mm (400/160 mils)	ø Probe tip: 0.78 mm (31 mils)		Axial single tip probe with spring-loaded measuring system. Simultaneous measurement of a double coating, i.e. paint over zinc on steel.
	- Austenitic steel	20 mm (0.8")	Suitable to measure so-called Duplex coatings (paint over zinc and zinc alloy on galvanized surfaces) on sheet metal or strips. Not suitable for thick, hot dipped galvanized coatings, because of
0.2 mm (8 mils) Fe	no	100 mm (4")	the nonhomogeneous alloy composition with unknown material properties and characteristics.
8 mm/6 mm (320/240 mils) at 100 μm (4 mils) Cu/lso 10 mm/6 mm (400/240 mils)	flat: ø 5.5 mm (220 mils)		Measurement of nonferrous metal coatings on nonconductive substrates (NF/NC) and nonferrous metal substrates (NF/NF).
at 230 µm (9 mils) Cr/Al	Polyamide 	16 mm (0.63")	Main application is to measure Cu-cladding thickness on PC-boards, also under a conformal coating; also measures the
0.9 mm (35 mils) CuZn	no	110 mm (4.3")	thickness of metal foils, as well as Cr-coatings on copper, aluminum or brass.
8 mm/4 mm (320/160 mils) at 60 µm (2.4 mils) Cu/lso 10 mm/4 mm (400/160 mils)	flat: ø 5.5 mm (220 mils)		
at 150 µm (6 mils) Cr/Al	Polyamide	16 mm (0.63")	Same application as ESC1 probe, however for thinner coatings.
 0.5 mm (20 mils) CuZn	no	110 mm (4.3")	
15 mm (600 mils)	no tip, flat: ø 15 mm (600 mils)	130 mm (5.2")	Axial single tip measurement probe with spring-loaded measuring
	Polyamide	18 mm (0.7")	element. Measures nonferrous metal coatings on nonmetal (NF/Iso) or on nonferrous metal substrate materials (NF/NF).
not relevant	no		Same applications as ESC1 probe, but for thicker coatings.

Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m. F: Measuring element protected against moist,	Description Order Number	Measurement accuracy u _s	Measurement point Ø for 10% error min. Ø	
aggressive media. T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible. * Note: Probe capability (accuracy and precision) tested under controlled conditions.	Measurement range	Measurement precision* s (the greater value applies)	Ø for 10% error min. Ø	
	EN3 602-305	0 - 0.25 mm : 0.002 mm 0.25 - 2 mm : 1 % 2 - 4 mm : < 2 % 1 - 15 μm : 0.3 μm 15 - 150 μm : 2 %	ø: 22 mm (870 mils) (NF/Fe) min. ø: 2 mm (80 mils) ø: 10 mm (400 mils) (Ni/NF) min. ø: 2 mm (80 mils)	
	0 - 4 mm (0 - 160 mils) (NF/Fe) 0 -150 μm	0 - 0.25 mm : 0.0003 mm 0.25 - 4 mm : < 0.5 % 1 - 20 μm : 0.2 μm	ø : 40 mm (1.6") (NF/Fe) min. ø : 50 mm (2") ø : < 10 mm (0.7") (Ni/NF)	
	(0 - 6 mils) (Ni/NF) ENW3 602-380	20 - 150 μm : 1 % 0 - 0.25 mm : 0.002 mm 0.25 - 2 mm : 1 % 2 - 4 mm : < 2 % 1 - 15 μm : 0.3 μm 15 - 150 μm : 2 %	min. ø: 50 mm (2") ø: 22 mm (870 mils) (NF/Fe) min. ø: 2 mm (80 mils) ø: 10 mm (400 mils) (Ni/NF) min. ø: 2 mm (80 mils)	
	0 - 4 mm (0 - 160 mils) (NF/Fe) 0 - 150 µm (0 - 6 mils) (Ni/NF)	0 - 0.25 mm : 0.0003 mm 0.25 - 4 mm : < 0.5 % 1 - 20 μm : 0.2 μm 20 - 150 μm : 1 %	ø : 40 mm (1.6") (NF/Fe) min. ø : 40 mm (1.6") ø : < 10 mm (0.7") (Ni/NF) min. ø : 40 mm (2")	

All probes can be connected to FISCHERSCOPE® MMS® Module NICKELSCOPE®

Characteristic values and technical data of probes for the



Probe can only be connected to FISCHERSCOPE® MMS® PCB

magnetic method



Ø for 10% error min. Ø	Probe tip radius	Height	
	Probe tip material	Diameter/width	Type of probe Application
D for 10% error	replaceable probe tip	Length (see page 24)	
ø : 22 mm (870 mils) min. ø : 2 mm (80 mils) ø : 8 mm (320 mils)	flat: 0.75 mm (30 mils)		Axial single tip probe with spring-loaded measuring system. Measurement of nonferrous metal coatings on steel and iron (NF/Fe) or electroplated nickel coatings on nonferrous substrates
min. ø : 2 mm (80 mils)	Heat treated steel	13 mm (0.5")	(Ni/NF). Ideally suited for the measurement of electroplated nickel coatings
D : 0.1 mm (4 mils) not relevant (Ni/NF)	no	80 mm (3.1")	on, for example: PC-board contacts, also under a thin coating of gold. Also used to measure thick NF metal coatings on steel, not subject to eddy current induced measurement errors in thick conductive coatings.
ø : 22 mm (870 mils) min. ø : 2 mm (80 mils) ø : 8 mm (320 mils)	flat: 0.75 mm (30 mils)	23 mm (0.9")	
min. ø: 2 mm (80 mils)	Heat treated steel	14 mm (0.6")	Single tip angle probe with spring-loaded measuring system. Same as probe EN3, however designed for measurements in pipes, bore holes or recesses.
D : 0.1 mm (4 mils) not relevant (Ni/NF)	no	72 mm (2.8")	, pipes, polo rioles di 16063563.

electrical conductivity method

: 8 x 8 mm (320 x 320 mils)	50 μm (2 mils)	130 mm (5")	
min. : 1 mm	Heat treated steel	32 mm (1.2")	Four-point probe measuring copper coating thicknesses on the surface of printed circuit boards according to the electric resistance method. No interference from underlying copper coatings separated by thin isolating layers.
not relevant	no		

Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m. F: Measuring element protected against moist,	Description Order Number	Measurement accuracy* u _s	Probe the Lift-off h Coating
aggressive media. T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible. * Note: Probe capability (accuracy and precision) tested under controlled conditions.	Measurement range	Measurement precision* s	Measurement point Ø for 10% error min. Ø
	ES1A ⁽¹⁾ 602-222	0.3 % of measured value	0 - 700 μm (28 mils)
	0.5 - 108 % IACS 0.3 - 63 MS/m	0.01 % IACS or 0.03 % of measured value	50 mm (200 mils) 2 mm (80 mils)
WASHING THE REAL PROPERTY.	ESW1A ⁽¹⁾ 602-389	0.3 % of measured value	0 - 700 μm (28 mils)
	0.5 - 108 % IACS 0.3 - 63 MS/m	0.01 % IACS or 0.03 % of measured value	50 mm (200 mils) 2 mm (80 mils)
	ES2 602-223	0.5 % of measured value	0 - 500 μm (20 mils)
	0.5 - 108 % IACS 0.3 - 63 MS/m	0.0 1% IACS or 0.05 % of measured value	36 mm (1400 mils) 2 mm (80 mils)
	S1A ⁽²⁾ 601-568	0.3 % of measured value	0 - 700 μm (28 mils)
	0.5 - 108% IACS 0.3 - 63 MS/m	0.01 % IACS or 0.03 % of measured value	50 mm (200 mils) 2 mm (80 mils)
110.000 1700	SW1A [©] 601-615	0.3 % of measured value	0 - 700 μm (28 mils)
	0.5 - 108% IACS 0.3 - 63 MS/m	0.01 % IACS or 0.03 % of measured value	50 mm (200 mils) 2 mm (80 mils)
	S2 ⁽³⁾ 601-569	0.5 % of measured value	0 - 500 μm (20 mils)
	0.5 - 108% IACS 0.3 - 63 MS/m	0.01 % IACS or 0.05 % of measured value	36 mm (1400 mils) 2 mm (80 mils)
	ES4B ⁽⁴⁾ ES40 ⁽⁵⁾ 602-539 603-235	0,3 % of measured value	0 - 500 μm (20 mils)
	0,5-108 % IACS 0,3-63 MS/m	0,01 % IACS or 0,03 % of measured value	30 mm (1.2") 1 mm (40 mils)

 $^{^{\}mbox{\tiny (1)}}$: Probe can only be connected to FISCHERSCOPE® MMS® module SIGMASCOPE® and module DUPLEX

⁽²⁾: Probe can only be connected to SIGMASCOPE® SMP1B

^{(3) :} Probe can only be connected to SIGMASCOPE® SMP2

^{(4):} Probe can only be connected to FISCHERSCOPE® MMS® EURO HF

electrical volume conductivity



Ø for 10% error min. Ø	Probe tip radius	Height	
	Probe tip material	Diameter/width	Type of probe Application
D for 10% error	replaceable probe tip	Length (see page 24)	
22 mm (870 mils) 15 mm (590 mils)	flat: ø 14 mm (550 mils)		Axial single tip probe with fixed measurement system. Used to measure volume conductivity of nonferrous metals.
	Polyamide	35 mm (1.4")	Used mainly in the aerospace industry, for NF-metal testing or processing. Also suitable to check heat treatment effects (material
0.91 mm (36 mils) at 52% IACS	no	130 mm (5.1")	strength) or to check for microstructural changes. A separate V-groove adapter has to be used on curved surfaces.
22 mm (870 mils) 15 mm (590 mils)	flat: ø 14 mm (550 mils)	40 mm (1.6")	Single tip angle probe with fixed measurement system.
	Polyamide	35 mm (1.4")	Same application as ES1A probe, however designed for measurements in pipes, bore holes or recesses. A separate
0.91 mm (36 mils) at 52% IACS	no	90 mm (3.5")	V-groove adapter has to be used on curved surfaces.
12 mm (470 mils) 5 mm (200 mils)	flat: ø 5.5 mm (220 mils)		Axial single tip probe with fixed measurement system.
	Polyamide		Same application as ES1A probe, however due to the higher measurement frequency especially suited for thinner specimen
0.44 mm (17 mils) at 52% IACS	no	110 mm (4.3")	(strips, sheet metal, coatings).
22 mm (870 mils) 15 mm (590 mils)	flat: ø 14 mm (550 mils)		
(**************************************	Polyamide	18 mm (0.7")	Axial single tip probe with fixed measurement system. Same application as ES1A probe, however only in conjunction
0.91 mm (36 mils) at 52% IACS	no	130 mm (5.1")	with the hand-held instruments SMP1B and SMP1BS.
22 mm (870 mils) 15 mm (590 mils)	flat: ø 14 mm (550 mils)	40 mm (1.6")	
	Polyamide	35 mm (1.4")	Single tip angle probe with fixed measurement system. Same application as S1A probe, however designed for measurements in pipes, bore holes and recesses.
0.91 mm (36 mils) at 52% IACS	no	90 mm (3.5")	Theastrements in pipes, sole holes and recesses.
12 mm (470 mils) 5 mm (200 mils)	flat: ø 5.5 mm (220 mils)		
· , ,	Polyamide	16 mm (0.6")	Axial single tip probe with fixed measurement system. Same application as ES2 probe, however only in conjunction with the hand-held instrument SMP2.
0.44 mm (17 mils) at 52% IACS	no	110 mm (4.3")	with the hallo-field instrument Siviez.
10 mm (400 mils) 5 mm (200 mils)	flat: ø 14 mm (550 mils)		Axial single-tip measurement probe with fixed measuring element. Measures the electrical conductivity of nonferrous metals according to the eddy current method. Applications include mate-
	Polyamide	18 mm (0.7")	rial sorting, heat treatment inspections and analysis of structural conditions. Suitable for the following measurement frequencies:
0.35 mm at 30 MS/m and 480 kHz	no	90 mm (3.5")	120 kHz, 240 kHz and 480 kHz. Measurement ES40 probe is additionally suited for a frequency of 60 kHz and contains an integrated temperature sensor.

- $\ensuremath{^{(5)}}$: Probe can only be connected to SIGMASCOPE® SMP10
- $^{\mbox{\tiny (6)}}$: Probe can only be connected to CU-SCOPE $^{\mbox{\tiny (8)}}$ CMP1A
- $^{\prime\prime}$: Probe can only be connected to FISCHERSCOPE® MMS Module DUPLEX


Note regarding probe designations: L: cable length for magnetic induction probes 5 m and for eddy current probes 3 m instead of 1.5 m. F: Measuring element protected against moist, aggressive media.	Description Order Number	Measurement accuracy* u _s	Measurement point Ø for 5% error min. Ø
T: Intermittent measurements on specimens with temperatures up to 100 °C (212 °F) possible. * Note: Probe capability (accuracy and precision) tested under controlled conditions.	Measurement range	Measurement precision* s	Ø for 5% error min. Ø
	EGAB1.3-FE	0 - 5 %Fe/5FN : 0.1 %FE/FN	ø : 15 mm (590 mils)
	602-221	5 %Fe/5FN - 80 %/110FN : 2 %	min. ø : 1 mm (80 mils)
	0.1 - 80 % Fe	0 - 10 %Fe/10FN : 0.05 %Fe/FN	ø : 30 mm (1.2")
	0.1 - 110 FN	10 %Fe/10FN - 80 %Fe/110FN : 0.5 %	min. ø : 10 mm (400 mils)
	EGABW1.3-FE 602-304 EGABW1.3L-FE 602-614	0 - 5 %Fe/5FN : 0.1 %FE/FN 5 %Fe/5FN - 80 %/110FN : 2 %	ø : 15 mm (590 mils) min. ø : 1 mm (40 mils)
	0.1 - 80 % Fe	0 - 10 %Fe/10FN : 0.05 %Fe/FN	ø : 36 mm (1.4")
	0.1 - 110 FN	10 %Fe/10FN - 80 %Fe/110FN : 0.5 %	min. ø : 18 mm (720 mils)
- Indiana -	EGABI1.3-150FE	0 - 5 %Fe/5FN : 0.1 %FE/FN	ø : 15 mm (590 mils)
	602-706	5 %Fe/5FN - 80 %/110FN : 2 %	min. ø : 2 mm (80 mils)
	0.1 - 80% Fe	0 - 10 %Fe/10FN : 0.05 %Fe/FN	ø : 30 mm (1.2")
	0.1 - 110 FN	10 %Fe/10FN - 68 %Fe/110FN : 0.5 %	min. ø : 9 mm (350 mils)

All probes can be connected to FISCHERSCOPE® MMS® module PERMASCOPE® and FERITSCOPE® MP30

- (1) : Measurement of Delta Ferrite content in sheet material. Thickness of the sheet material.
- ⁽²⁾: Measurement of Delta Ferrite content in clad layers. Thickness of the cladding.


Comments to probe dimensions:

Listed are the maximum diameter (respective to width) and the maximum height of the probe, as well as the overall length from the probe tip to the cable entry point.



the ferrite content

Ø for 5% error min. Ø	Probe tip radius	Height	
D for 5% error* D for 10% error**	Probe tip material	Diameter/width	Type of probe Application
	replaceable probe tip	Length (see page 24)	
ø : 10 mm (400 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)		Axial single tip probe with spring-loaded measuring system. Measurement of the Delta Ferrite content in ferrite percent or WRC ferrite number. Suitable for the measurement of delta ferrite content in weld metal and clad layers of austenitic or Duplex stainless steel. Also used to determine the ratio of martensite in austenitic stainless steels.
D : 1 mm (40 mils) D : 1 mm (40 mils)	PVD coated	10 mm (0.4")	
	yes	110 mm (4.3")	
ø : 10 mm (400 mils) min. ø : 2 mm (80 mils) D : 1 mm (40 mils) D : 1 mm (40 mils)	0.75 mm (30 mils)	23 mm (0.9")	Single pole angle probe with spring-loaded measuring system. Same application as EGAB1.3-FE probe, however preferred for measurements in pipes, bore holes or recesses.
	PVD coated	14 mm (0.6")	
	yes	72 mm (2.8")	
ø : 10 mm (400 mils) min. ø : 2 mm (80 mils)	0.75 mm (30 mils)	6.5 mm (0.26")	Single tip probe for inside measurements with spring-loaded measuring system. Same application as EGAB1.3-FE probe, however designed for measurements in pipes, bore holes and grooves. Externally triggered measurement acquisition should be used when measuring small inside diameters to prevent measurement errors. Maximum insertion depth: 320 mm (12.8").
D : 1 mm (40 mils) D : 1 mm (40 mils)	PVD coated	5.5 mm (0.22")	
	yes	320 mm (12.6")	



Accessories

For the accurate measurement of coating thickness on small parts, such as fasteners, stampings, sleeves, etc. or parts with complex geometry. Probe specific mounting adapters are required.

*: included with standard V12 measurement stand (order number 602-260) or V12-SP stand (order number 602-262)



V12 measurement stand with base* and adapter 600-796* to mount the following probes:

- ETA3.3H, ETA3.3F, ETA3.3T
- EGAB1.3-SD
- V6EKB4



V12 measurement stand with magnetic shuttle table 600-019 and adapter 600-173* to mount the following probes:

- EGA2H
- EN3



Screw measurement device for accurate measurements of coating thicknesses on metallic fasteners according to ISO DIN 4042.



V12 measurement stand with V-table*, adapter 600-173* and adapter 600-077 to mount the following probes:

- EGABW1.3, EGBW2, EGABW1.3FE
- EAW3.3, EA9
- ENW3



V12 measurement stand with V-table*, adapter 600-173* and adapter 601-691 to mount the following probes:

- EGABI1.3-150, EGABI1.3-260, V1EKB4, V1EKB10, EGABI1.3-150FE
- EAI3.3-150



Measuring stand V12 mot. MP for automated measurements specifically for paint coatings without indentation- or positioning errors.



V12 measurement stand with adapter 600-213 to mount the following probes:

- ESD1, ESD2
- ESC1, ESC2
- ES2



V12-SP measurement stand with quick loading screw fixture and adapter 602-370* to mount the following probes:

• EGAB1.3, EGB2, EGAB1.3FE



Measuring head MD4 for automatic measurements of coatings on ferromagnetic substrate materials. Easy integration into production lines for 100% testing.



A series of hand-held and bench top instruments are available for the probes listed. For magnetic induction based measurement the DELTASCOPE® MPxC series is used, the ISOSCOPE® MP series is used for eddy current

coating thickness measurement, the DUALSCOPE® MP20 and MP40 series combine the magnetic induction and eddy current methods.



DELTASCOPE® MP10 displays individual measurement values without statistics, it has no serial interface (no printing, no data transfer) and does not store measurement values.



DUALSCOPE® MP20 with statistical measurement series evaluation capability. Does not store measurements, it has no serial interface.



Measurement of the paint coating thickness on a curved surface using ETD3.3 probe and DUALSCOPE® MP40.



Measurement of a duplex coating (paint/zinc coating on iron) using EDX10 probe and DUALSCOPE® MP40.



Measurement system Fischerscope® MMS with various methods for coating thickness measurement and material testing.



Hand-held NICKELSCOPE® NMP2 for the measurement of nickel or nonferrous metal coating on steel, as well as nonferrous metal coatings on nonconductive substrates.



The CU-SCOPE CMP1A is used to measure copper plating thickness in PCB through holes.



SIGMASCOPE® SMP10 for measuring the electrical conductivity of nonferromagnetic, electrically conducting metals.



The FERITSCOPE® MP30 determines the delta ferrite content in austenitic weld metal or duplex stainless steel.